



CENCORE 4710 HDPE MATERIAL DATA SHEET

CENCORE 4710 HDPE MEETS OR EXCEEDS:
 ASTM D 2737
 ASTM D 2239
 ASTM D 3350, CELL CLASSIFICATION PE 445576C

CENCORE 4710 PIPE FOR:
 POTABLE WATER APPLICATIONS.

NOMINAL PIPE PROPERTIES

	ASTM METHOD	ENGLISH UNITS	SI UNITS
DENSITY	D 4883	-	.959 g/cc
MELT INDEX ¹	D 1238	-	8.5g/10 min
HYDROSTATIC DESIGN BASIS @ (23° C)	D 2837	1600 psi	11.0 MPa
HYDROSTATIC DESIGN BASIS @ (60° C)	D 2837	1000 psi	6.9 MPa
CARBON BLACK CONCENTRATION	D 1603	2.30%	2.30%

NOMINAL RAW MATERIAL PROPERTIES

TENSILE STRENGTH			
@ YIELD (2 in/min)	D 638	3625 psi	25.0 MPa
@ BREAK (2 in/min)	D 638	5500 psi	38.0 MPa
ELONGATION			
@ BREAK (2 in/min)	D 638	>600%	>600%
FLEXURAL MODULUS ²	D 790	150,000 psi	1,035 MPa
NOTCHED IZOD IMPACT STRENGTH	D 256	9.0 ft-lbf/in	0.49 kJ/m
HARDNESS (SHORE D)	D 2240	66	66
VICAT SOFTENING POINT	D 1525	259° F	126° C
BRITTLENESS TEMPERATURE	D 746	<-180° F	<-118° C
ENVIRONMENTAL STRESS CRACK RESISTANCE ³	D 1693	>5000 hrs.	>5000 hrs.
NOTCH TENSILE (PENT)	F 1473	>10,000 hrs.	>10,000 hrs.
CELL CLASSIFICATION	D 3350	445576C	445576C

¹ 190°C/21600 g

² 2% Secant-Method 1

³ Condition C

Available in Iron Pipe Size 1/2" - 2".

Centennial Plastics is an ISO 9001 certified company.

CenCore 4710 is certified by NSF.

CenCore meets AWWA C901 Requirements.

CenCore 4710 is certified by NSF Standards 14 and 61.



(3 1 7) 3 4 6 - 4 1 1 0
 www.drainagesolutionsinc.com

CENTENNIAL PLASTICS INC. | 1830 CENTENNIAL AVENUE | HASTINGS, NE 68901
 PHONE: (866) 851-2227 | FAX: (402) 462-5529
 WWW.CENTENNIALPLASTICS.COM

**Effective Jan. 30, 2014
 Supersedes Aug. 14, 2014**