




Mirafi® 600X

Mirafi® 600X is a woven geotextile composed of polypropylene fibers, which are woven into a stable network such that the fibers retain their relative position. Mirafi® 600X is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids. Mirafi® 600X meets AASHTO M288 Strength Classes 1, 2, & 3 for Elongation < 50%.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)). [NTPEP](#) Listed

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	315 (1402)	315 (1402)
Grab Tensile Elongation	ASTM D4632	%	15	15
Trapezoid Tear Strength	ASTM D4533	lbs (N)	120 (534)	120 (534)
CBR Puncture Strength	ASTM D6241	lbs (N)	900 (4005)	
			MAXIMUM OPENING SIZE	
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	40 (0.425)	
			MINIMUM ROLL VALUE	
Permittivity	ASTM D4491	sec ⁻¹	0.05	
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	4 (163)	
			MINIMUM TEST VALUE	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	
PHYSICAL PROPERTIES	UNIT		ROLL SIZE	
Roll Dimensions (width x length)	ft (m)		12.5 x 360 (3.8 x 110) 15 x 300 (4.6 x 91) 17.5 x 254 (5.3 x 78.7)	
Roll Area	yd ² (m ²)		500 (418)	
Roll Weight	lbs (kg)		208 (94)	
Label Color				

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi® is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved
FGS000393
ETQR 39