

WINFAB 1211

WINFAB 1211 is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.

WINFAB 1211 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	124 x 124 lbs	551.6 x 551.6 N
Elongation	ASTM D-4632	15%	15%
CBR Puncture	ASTM D-6241	325 lbs	1446 N
Trapezoidal Tear	ASTM D-4533	65 x 65 lbs	289.1 x 289.1 N
UV Resistance (500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	30 US Std. Sieve	0.60 mm
Permittivity	ASTM D-4491	0.05 sec ⁻¹	0.05 sec ⁻¹
Water Flow Rate	ASTM D-4491	10 gpm/ft ²	407.4 lpm/m ²

*Maximum Average Roll Valve

Notes:

- Mullen Burst ASTM D-3786 has been removed. It is not recognized by ASTM D-35 on Geosynthetics.
- Puncture ASTM D-4833 has been removed. It is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D-6241

PROPERTY	Typical English	Typical Metric
Roll Dimensions	36 in x 1200 yds	.91 m x 1097 m
	36 in x Custom	.91 m x Custom
	42 in x 1200 yds	1.07 m x 1097 m
	42 in x Custom	1.07 m x Custom
	48 in x 1200 yds	1.22 m x 1097 m
	48 in x Custom	1.22 m x Custom

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2013 Willacoochee Industrial Fabrics, Inc.