

WINFAB 2098

WINFAB 2098 is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position.

WINFAB 2098 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV English	MARV Metric
Tensile Strength (Grab)	ASTM D-4632	260 x 180 lbs	1155 x 800 N
Elongation	ASTM D-4632	15 x 15%	15 x 15%
UV Resistance (500 hrs)	ASTM D-4355	80%	80%
Apparent Opening Size (AOS)*	ASTM D-4751	30 US Std. Sieve	0.60 mm
Mullen Burst	ASTM D-3786	175 psi	1200 kPa
Water Flow Rate	ASTM D-4491	75 gpm/ft ²	3045 lpm/m ²

*Maximum Average Roll Valve

PROPERTY	Typical English	Typical Metric
Roll Dimensions	36 in x 330 ft 36 in x 2250 ft	.914 x 914.4 m .914 x 100.58 m

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2013 Willacoochee Industrial Fabrics, Inc.



(317) 346-4110

DRAINAGE SOLUTIONS, INC www.drainagesolutionsinc.com

