

WINGRID BX11



WINGRID BX11 is a punched and drawn polypropylene geogrid product that is intergrally formed into a biaxial geogrid.

WINGRID BX11 resists ultraviolet deterioration, rotting, and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	MARV English	MARV Metric
Aperture Dimensions ²	1.0 x 1.3 in	25 mm x 33 mm
Minimum Rib Thickness ²	.03 in x .03 in	.76 x .76 mm
Ultimate Tensile Strength ³	850 x 1300 lbs/ft	12.4 x 19.0 kN/m
Tensile Strength at 2% Strain ³	280 x 450 lbs/ft	4.1 x 6.6 kN/m
Tensile Strength at 5% Strain ³	580 x 920 lbs/ft	8.5 x 13.4 kN/m
Junction Efficiency ⁴	93%	93%
Flexural Stiffness ⁵	250,000 mg-cm	250,000 mg-cm
Aperture Stability ⁶	.32 m-N/deg	.32 m-N/deg
Resistance to Installation Damage ⁷	95%SC/93%SW/90%GP	95%SC/93%SW/90%GP
Resistance to Long Term Degradation ⁸	100%	100%
UV Resistance (500 hrs) ⁹	100%	100%

Notes:

- 1. Unless notified otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759-02. Brief descriptions of test procedures are given in the following notes.
- 2. Nominal dimensions.
- 3. True resistance to elongation when initially subjected to a load determined in accordance with ASTM D6637-01 without deforming test materials under load before measuring such resistance or employing "secant" or "offset" tangent methods of measurement so as to overstate tensile properties.
- 4. Load transfer capability determined in accordance with GRI-GG2-05 and expressed as a percentage of ultimate tensile strength.
- 5. Resistance to bending force determined in accordance with ASTM D5732-01, using specimens of width two ribs wide, with transverse ribs cut flush with exterior edges of longitudinal ribs (as a "ladder"), and of length sufficiently long to enable measurement of the overhang dimension.
- 6. Resistance to in-plane rotational movement measured by applying a 20 kg-cm (2 m-N) moment to the central junction of a 9 inch x 9 inch specimen restrained at its perimeter in accordance with the U.S. Army Corps of Engineers Methodology for measurement of Torsional Rigidity.
- 7. Resistance to loss of load capacity or structural integrity when subjected to mechanical installation stress in clayey sand (SC), well graded sand (SW), and crushed stone classified as poorly graded gravel (GP). The geogrid shall be sampled in accordance with ASTM D6637-01.
- 8. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing.
- 9. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355-05.

PROPERTY	Typical English	Typical Metric
Roll Dimensions	12.95 x 246 ft	3.95 x 75 m

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. Willacoochee Industrial Fabrics disclaims any and all implied, expressed, or statutory standards, guarantees, or warranties. This includes without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.

© 2013 Willacoochee Industrial Fabrics, Inc.



(317) 346-4110
www.drainagesolutionsinc.com

